



HAL
open science

Dynamical Facilitation Governs the Equilibration Dynamics of Glasses

Rahul Chacko, François P. Landes, Giulio Biroli, Olivier Dauchot, Andrea
Liu, David Reichman

► **To cite this version:**

Rahul Chacko, François P. Landes, Giulio Biroli, Olivier Dauchot, Andrea Liu, et al.. Dynamical Facilitation Governs the Equilibration Dynamics of Glasses. 2024. hal-04379217

HAL Id: hal-04379217

<https://inria.hal.science/hal-04379217>

Preprint submitted on 8 Jan 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution 4.0 International License

Dynamical Facilitation Governs the Equilibration Dynamics of Glasses

Rahul N. Chacko,¹ François P. Landes,² Giulio Biroli,³ Olivier Dauchot,⁴ Andrea J. Liu,¹ and David R. Reichman⁵

¹*Department of Physics and Astronomy, University of Pennsylvania, Philadelphia, Pennsylvania 19104, USA*

²*Université Paris-Saclay, CNRS, Laboratoire Interdisciplinaire des Sciences du Numérique, 91400, Orsay, France*

³*Laboratoire de Physique de l'École Normale Supérieure,
ENS, Université PSL, CNRS, Sorbonne Université,*

Université Paris-Diderot, Sorbonne Paris Cité, 75005 Paris, France

⁴*UMR Gulliver 7083 CNRS, ESPCI, PSL Research University, 10 rue Vauquelin, 75005 Paris, France*

⁵*Department of Chemistry, Columbia University,
3000 Broadway, New York, New York 10027, USA*

(Dated: December 27, 2023)

Convincing evidence of domain growth in the heating of ultrastable glasses suggests that the equilibration dynamics of super-cooled liquids could be driven by a nucleation and growth mechanism. We investigate this possibility by simulating the equilibration dynamics of a model glass during both heating and cooling between poorly and well-annealed states. Though we do observe the growth of domains during heating, we find that domains are absent during cooling. This absence is inconsistent with classical nucleation theory. By comparing the equilibration dynamics of our glass with that of two models with kinetic constraints, we demonstrate that dynamical facilitation generically leads to heating driven by domain growth and cooling without domains. Our results provide strong evidence that dynamical facilitation, not nucleation and interfacial-tension-driven domain growth, is the driving mechanism for the equilibration dynamics of glass-formers.

I. INTRODUCTION

The phenomenology of glasses and supercooled liquids (*i.e.*, glasses in metastable equilibrium such that detailed balance is satisfied on all relevant time scales) bears a striking resemblance to that of crystalline solids [1–8]. As with transformations of Eshelby disclinations in crystals [9], local plastic events in these systems perturb their neighborhoods with long-ranged quadrupolar displacement fields [10, 11]. A large body of experimental evidence also finds that ultrastable glasses evolve upon heating in a manner consistent with the Avrami framework of classical nucleation theory [12]: fronts of high-temperature supercooled liquid advance at constant speed into the bulk ultrastable glass [5, 13–29], with the fraction of material retaining ultrastable glass structure decaying with time according to a compressed exponential law [15, 16, 18, 30]. By contrast, poorly-annealed (“ordinary”) glasses are found to transform homogeneously into the supercooled liquid upon heating above the glass transition temperature [20, 27]. This difference of behavior, also observed in pressure-controlled molecular dynamics (MD) simulations [7, 8, 30, 31], raises the possibility that a thermodynamic first-order transition mediated by nucleation and domain growth separates poorly-annealed glass from well-annealed glass [6–8, 32, 33], as in the case of crystal freezing and melting.

Indeed, as with crystals, a notion of structural order also applies to supercooled liquids. In these amorphous systems, local equilibrium structure constrains [34] and is constrained by [35] neighboring structure up to a finite distance ξ_{PTS} (the “point-to-set” length) away [36]. Random First Order Transition Theory (RFOT), known to be exact in infinite dimension [37], predicts systems below a critical temperature T_{MCT} to be separated into a

mosaic of ξ_{PTS} -sized domains of mutually-incompatible amorphous order [1, 36, 38]. As demonstrated by randomly pinned glasses [39] and supercooled liquids coupled to a reference configuration [3], amorphous order can in principle lead to first order transitions in amorphous systems, supporting the possibility of a first-order transition in supercooled liquids [40].

Nucleation and domain growth is not the only available explanation for the equilibration dynamics of glass-formers, however. Particles in supercooled liquids are trapped into “cages” by their nearest neighbors, rattling around for long periods between cage-escape events in which they hop out of one cage and into another [41, 42]. As a local plastic event within an otherwise elastic material, a cage escape weakens its neighborhood, creating the conditions for more cage escapes [11]. Such a process, in which rearrangements propagate mobility to their local neighborhoods, is known as dynamical facilitation [43, 44] and plays an important role in glassy liquids [45]. This self-propagation of mobility results in avalanches of plastic events correlated in space and time [42]. On long time scales, these avalanches appear as large clusters of spatially-correlated mobility that grow as a function of time scale [43, 46], resembling domain growth. Dynamical facilitation plays an important role in the equilibrium dynamics of supercooled liquids, and it could also be the key mechanism at play in *equilibration dynamics*, *i.e.* relaxation towards equilibrium. Indeed, many of the phenomena observed in glasses upon heating or cooling are also seen in Kinetically Constrained Models (KCMs), spin lattice models in which spins interact only via facilitation [47], upon heating [2, 48, 49] or cooling [50]. Dynamical facilitation therefore offers a possible alternative explanation for the behavior of glasses during heating and cooling. In this paper, we show that it is indeed dynamical

ical facilitation that governs the equilibration dynamics of glasses, not nucleation followed by domain growth.

We first address the question of nucleation, interpreted in the classical sense [51] of a competition between bulk and interfacial free energies which sets a critical size above which randomly-nucleated domains will grow and below which they will shrink. We distinguish nucleation, which involves a thermodynamic drive towards domain growth as small domains (of linear size smaller than the nucleation length) are suppressed, from the evolution of structure via random, thermally-activated rearrangements, with no suppression of small domains. In the latter case, an additional mechanism is required to explain domain growth. In the second part of this paper, we show that dynamical facilitation fills this role.

We conduct MD simulations of a polydisperse glass at fixed temperature T_∞ and pressure P for two types of initial condition. In experiments using the first type of initial condition, which we refer to as *homogeneous experiments*, the initial state corresponds to equilibrium at an initial temperature T_0 different from the thermostat temperature T_∞ . In experiments using the second type of initial condition, which we refer to as *slab experiments*, we introduce a system-percolating slab of T_∞ equilibrium structure lying in the $x \equiv 0$ plane that interrupts the T_0 structure of the surrounding system (see Figs. 4(a) and 4(b)). In this geometry, the slab can expand while keeping the size and shape of its boundary fixed, avoiding any putative interfacial free energy cost as it expands. In a classical nucleation theory scenario, the slab represents a nucleus above the critical nucleus size. We fix $T_{\text{low}} = \min\{T_0, T_\infty\}$ and $T_{\text{high}} = \max\{T_0, T_\infty\}$ so that any critical point separating T_0 and T_∞ during heating will also do so during cooling. These simulations provide a number of tests for nucleation and domain growth:

1. We can characterize the local structure and dynamics, and simply look (by eye) for growing domains of T_∞ structure in individual realizations of the homogeneous experiment.
2. We can also look for evidence of a nucleation time in these experiments.
3. We can quantitatively track domain growth via the displacement of the slab boundary in slab experiments.
4. We can assess the roughness of domains, both qualitatively in individual realizations of the homogeneous experiment and quantitatively (via the width of the slab boundary) in the slab experiment.

As we will show, all four tests argue against nucleation, with the most striking evidence provided by the absence of domain growth during cooling, as we shall discuss. Before applying this methodology to our polydisperse model glass, we validate these tests by applying them to a crystallizing monodisperse system with temperatures T_{low} and T_{high} straddling its melting point, verifying our

expectations for the case of a genuine first order transition.

After testing the nucleation and growth mechanism and obtaining results inconsistent with it, we support our claim that dynamical facilitation is responsible for the equilibration dynamics of glasses by applying the same four tests to two plaquette models, the Triangular Plaquette Model (TPM) [50, 52, 53] and the Square Pyramidal Plaquette Model (SPPM) [54]. Plaquette models are spin lattice models with a dual representation in terms of plaquettes with trivial thermodynamics and kinetically-constrained dynamics [55], corresponding to KCMs in the plaquette representation. The TPM and SPPM are similar by design, and the mechanisms underlying dynamical facilitation in these two systems differ greatly from the elastoplastic mechanism for facilitation in supercooled liquids and glasses [11]. We find that just like our polydisperse model glass, these plaquette models exhibit domain growth during heating and none during cooling. For all three systems, domain growth during heating proceeds at a constant speed that persists even as the system relaxes. The only notable difference between the systems is the evolution of domain roughness, which is different for all three systems and therefore not a test for facilitation-driven dynamics.

II. SYSTEM

Our three-dimensional monodisperse crystal and two-dimensional polydisperse glass systems comprise particles of uniform mass m interacting via the pair potential

$$V(\tilde{r}) = \begin{cases} V_0 (\tilde{r}^{-12} + c_0 + c_2 \tilde{r}^2 + c_4 \tilde{r}^4) & \tilde{r} \leq 1.25, \\ 0 & \tilde{r} > 1.25, \end{cases} \quad (1)$$

where

$$\tilde{r} = 2r / [(\sigma_i + \sigma_j)(1 - 0.2|\sigma_i - \sigma_j|)].$$

Here, r is the separation between particles i and j with sizes σ_i and σ_j , and the constants c_0 , c_2 , and c_4 are chosen such that $V(1.25) = V'(1.25) = V''(1.25) = 0$ (§A 1). Following [56], for the polydisperse system, σ_i for each particle is drawn independently from a distribution with probability density $\propto \sigma^{-3}$ in the interval $[\sigma_{\text{min}}, \sigma_{\text{max}}]$, with σ_{min} and σ_{max} chosen such that the coefficient of variation of σ is $c_\sigma = 0.23$. This system, introduced in [56], is designed to allow equilibration to temperatures well below T_{MCT} using swap Monte Carlo simulations. We take V_0 , $\bar{\sigma}$, m , and V_0/k_B to be our energy, length, mass, and temperature units, where k_B is the Boltzmann constant and where $\bar{\sigma}$ is the expected value of the particle diameter distribution. The system coordinates are centered at the origin and periodic boundary conditions are imposed along each axis of the system.

We prepare our initial states using constant-volume Monte Carlo simulations implemented as described in

§A 2. For the monodisperse case, the homogeneous experiments have $N = 27648$ particles and initial lengths 48, $12\sqrt{3}$, and $8\sqrt{6}$ along the x , y and z axes respectively, corresponding to number density $\rho = \sqrt{2}$. These system dimensions are compatible with a perfect FCC crystal, the ground state for this system (§A 7). For melting, we heat the system from an initial configuration equilibrated to $T_{\text{low}} = 1.90$ using a thermostat at $T_{\text{high}} = 2.35$, while for freezing, we cool the system from an initial configuration equilibrated to $T_{\text{high}} = 2.10$ using a thermostat at $T_{\text{low}} = 1.48$.

For the slab experiments in the monodisperse system, we fix $T_{\text{low}} = 2.0$ and $T_{\text{high}} = 2.1$, which straddle the melting point. We preserve the compatibility of the system dimensions with a perfect FCC crystal by not attempting to eliminate the initial pressure gradient at the slab boundary in slab experiments, other than by our choice of narrowly-separated T_{low} and T_{high} . Instead, we double the number of particles and the system size along the x -axis, as compared to the systems used for homogeneous experiments. This allows for time between the early-time pressure wave dissipating and the left and right slab fronts colliding at the periodic boundary of the system. For freezing, we define our frozen slab to be the region with x -coordinate satisfying $|x| < 6$. For melting, our preparation protocol (§A 2) requires us to specify the size of the frozen non-slab region instead, leaving the size of the melted slab region to be an emergent property of our preparation protocol dependent on the size of the interface. We define the non-slab region to be that with x -coordinate satisfying $|x| \geq 8$.

For the polydisperse case, we simulate $N = 20000$ particles and fix $T_{\text{low}} = 0.06$ and $T_{\text{high}} = 0.14$ for both homogeneous and slab experiments. The homogeneous heating experiments have initial lengths 200.00 and 100.00 along the x and y axes respectively, corresponding to number density $\rho = 1$. At this density, $T_{\text{MCT}} \approx 0.12$ [46], such that (accounting for density changes [57]) T_{low} and T_{high} straddle T_{MCT} . The homogeneous heating experiments follow these systems to steady state at T_{high} , corresponding to (average) system lengths 204.70 and 102.35 ($\rho \approx 0.955$) along the x and y axes. These T_{high} equilibrium configurations are then used as the initial $T_0 = T_{\text{high}}$ states for the homogeneous cooling experiments.

Our choice of $T_{\text{low}} = 0.06$ and $T_{\text{high}} = 0.14$ comes from practical considerations. We require $T_{\text{low}} < T_{\text{MCT}}$ to ensure that T_{low} is low enough for facilitation to play an important role in the equilibrium dynamics [43] and for amorphous order to set in [1, 38]. The lower we set T_{low} , the stronger we expect dynamical facilitation to be and the slower we expect the dynamics to be. We choose $T_{\text{low}} = 0.06$ as a compromise between strong facilitation and dynamics fast enough that we are able to see appreciable structural evolution on the time scale of a week of run time. We have checked that increasing T_{high} , even above the onset temperature, does not affect our results. However, choosing $T_{\text{high}} = 0.14$, below the onset temperature, ensures that we are probing a

potential ultrastable-to-poorly-annealed glass transition, rather than a transition between an ultrastable glass and a high temperature liquid.

For the slab experiments in the polydisperse system, we define the slab to be the region satisfying $|x| < b$, where $b = 25.00$ for heating and 25.56 for cooling. In slab experiments, we greatly reduce the initial pressure gradient at the slab boundary by first equilibrating the system in its entirety to T_{∞} , with system dimensions 200.00 and 100.00 if $T_{\infty} = T_{\text{low}}$ or 204.70 and 102.35 if $T_{\infty} = T_{\text{high}}$, then shrinking or stretching the non-slab region along the x -axis such that $\rho \approx 0.955$ in this region if $T_0 = T_{\text{high}}$ or $\rho = 1$ if $T_0 = T_{\text{low}}$, before finally evolving this non-slab region with Monte Carlo moves at temperature T_0 until it reaches steady state.

Our MD simulations are performed in LAMMPS [58] (see §A 3), adopting a Nosé-Hoover thermostat and a Berendsen barostat that keeps the relative sizes of the system along each axis constant. In order to minimize the perturbation to the system due to the start-up of the barostat, we fix the pressure such that the virial contribution to the pressure at the beginning of the MD simulation matches that of the target T_{∞} equilibrium state. For any given MD experiment, we average our results over 100 realizations, except when explicitly considering individual realizations or when performing the homogeneous experiments on the polydisperse glass, in which case we average over only 10 realizations.

We define time $t = 0$ as the time at which the MD simulations begin. For our analysis, it will be necessary to measure the distributions of structural and dynamical quantities in the initial, untransformed state during homogeneous experiments, as well as at equilibrium at the target temperature T_{∞} . Our methodology for obtaining these distributions can be found in §A 4.

III. CRYSTAL CASE STUDY

We first validate our tests by applying them to the first-order melting and freezing transitions of a monodisperse system of particles, in which the growth of nuclei is driven by bulk free energy differences [59], with structural frustration at the boundary of the nucleus suppressing roughness and promoting domain growth [60, 61]. We track the evolution of structure in this system using Tong and Tanaka's Θ order parameter [62], a local measure of packing inefficiency that vanishes in the limit of perfect FCC structure. We also track the corresponding evolution of the mobility $\mu(t)$, defined here for each particle as the magnitude of its inherent state displacement between times t and $t + 0.1$.

Test 1: Here we simply look for the emergence and growth of T_{∞} -structure domains in individual realizations of the homogeneous experiment. Figs. 1(a) for melting and 1(e) for freezing (see also §B 4) both show a domain of T_{∞} structure and dynamics which grows to span the system along the narrow horizontal axis. At this




FIG. 1. Crystal melting (a–d) and freezing (e–h) transitions in a monodisperse system. (a, e): snapshots in the $z \equiv 0$ plane of (top row) the Θ order parameter and (bottom row) the mobility μ as a nucleus appears and grows in an individual trajectory. (b, c, f, g): distributions (b, f) $P(\log_{10} \Theta)$ and (c, g) $P(\log_{10} \mu)$ at times (b, c) $t = 100, 200, \dots, 600$ and (f, g) $t = 1000, 2000, \dots, 7000$ (later time, lighter color). The red curves in (b) and (c) are equilibrium distributions. (d, h): untransformed fraction $1 - f$ for f calculated from $P(\log_{10} \Theta)$ (dashed red), $P(\log_{10} \mu)$ (dashed green), potential energy \overline{V} (solid orange), inherent state potential energy \overline{V}_{IS} (solid blue), $\overline{\Theta}$ (solid red), $\log_{10} \overline{\Theta}$ (dotted red), $\overline{\mu}$ (solid green), and $\log_{10} \overline{\mu}$ (dotted green).

point, the domain can expand without gaining any more interfacial area, making this width an upper bound for the critical nucleus size, and we see the domain quickly grow to envelop the entire system.

Test 2: Here we look for evidence of a waiting time for nucleation. In Fig. 1(a), we see that the time between forming a system-spanning nucleus and melting the entire system is of order $t \sim 10^0$, while it takes a time of order $t \sim 10^2$ for this system-spanning nucleus to appear. For cooling (Fig. 1(e)) these time scales are $t \sim 10^2$ and $t \sim 10^3$, respectively. This scale separation between the nucleation and domain growth times holds true across realizations (§VI).

Two-state scenario: Our third and fourth tests involve slab experiments. To ensure that results from these are relevant to systems without an artificial slab, we first demonstrate that the structural evolution observed in the homogeneous experiments corresponds to a two-state scenario, such that at any time t , a fraction f of the system has local structure distributed according to equilibrium at the thermostat temperature T_∞ (the target state), while the remaining fraction $1-f$ retains its initial distribution of structure, corresponding to equilibrium at temperature T_0 (the initial state). In this scenario, the distribution $P(\phi, t)$ of a local structural indicator ϕ with initial-state distribution $P_0(\phi)$ and target-state distribution $P_\infty(\phi)$ will evolve according to

$$P(\phi, t) = (1 - f(t)) P_0(\phi) + f(t) P_\infty(\phi), \quad (2)$$

interpolating between $P_0(\phi)$ and $P_\infty(\phi)$ as the transformed fraction f grows with time. Given distributions $P_0(\phi)$, $P_\infty(\phi)$, and $P(\phi, t)$ for a structural quantity ϕ , we can extract the transformed fraction f from $P(\phi, t)$ under the assumption that Eq. 2 holds (see §A 8). Alternatively, Eq. 2 implies that

$$1 - f(t) = \frac{\bar{\phi}_\infty - \bar{\phi}(t)}{\bar{\phi}_\infty - \bar{\phi}_0}, \quad (3)$$

where $\bar{\phi}_0$, $\bar{\phi}_\infty$, and $\bar{\phi}(t)$ are the mean values of the quantity ϕ distributed according to $P_0(\phi)$, $P_\infty(\phi)$, and $P(\phi, t)$, respectively, allowing us to calculate f from the evolving mean of ϕ .

If the two-state scenario holds, we should obtain the same value for the transformed fraction f , regardless of whether we use the distribution $P(\phi, t)$ or the mean $\bar{\phi}(t)$ to calculate it, and regardless of which local structural variable ϕ we choose. We can therefore test the validity of the two-state scenario by calculating f from both $P(\phi, t)$ and $\bar{\phi}$ for a variety of different structural quantities ϕ . In practice, we only calculate f from $P(\phi, t)$ for a single structural quantity ϕ , since this is more complicated to do (§A 8). Though it is not a requirement of the two-state equilibration scenario, we also check if we can obtain f from $P(\phi, t)$ and $\bar{\phi}$ when ϕ is a dynamical, rather than structural, quantity, since the coupling of structure and dynamics is a question of physical interest.

In Figs. 1(b), 1(c), 1(f), and 1(g), we see that the T_0 and T_∞ distributions of $\log_{10} \Theta$ and $\log_{10} \mu$ are well-separated [63], making the validity of the two-state scenario immediately apparent. We calculate $1-f$ from these distributions and plot the resulting curves against $1-f$ calculated from $\bar{\phi}$ for ϕ corresponding to Θ , $\log_{10} \Theta$, μ , $\log_{10} \mu$, the potential energy V associated with each particle, and the inherent state potential energy V_{IS} associated with each particle. As shown in Figs. 1(d) and 1(h), these different methods of calculating $1-f$ agree well with one another, confirming validity of the two-state scenario and therefore the soundness of the slab experiment as a test for domain growth, and showing that structure and dynamics are coupled together in crystal freezing and melting.

Having validated the slab experiments, we calculate the (ensemble-averaged) Θ profile along the x -axis, shown as transparent curves in Figs. 2(c) and 2(d). We identify the interface at the boundary between a T_∞ structure slab and the surrounding T_0 structure region by fitting this profile with a logistic function

$$\Theta(\tilde{x}) = \frac{\Theta_\infty + \Theta_0}{2} + \frac{\Theta_\infty - \Theta_0}{2} \tanh \frac{\tilde{x} - x_*}{2\lambda}, \quad (4)$$

where the argument $\tilde{x} = 2|x|/L_x$ accounts for changes in L_x (the system size along x) due to the barostat and takes advantage of the $x \mapsto -x$ symmetry of our slab geometry [64]. The parameters Θ_∞ , Θ_0 , x_* , and λ are fit at each snapshot of time t , representing, respectively, the plateau value of Θ within the slab of T_∞ structure, the plateau value of Θ outside this slab, the interface center, and the interface width. The order parameter Θ is invariant with respect to isotropic expansion, and is therefore insensitive to the transient effect of the pressure gradient at time $t = 0$, making it an especially suitable choice for our analysis.

Test 3: Here we check for domain growth in the slab experiment. As we see in Figs. 2(c) and 2(d), the slab of T_∞ structure indeed grows in both melting and freezing experiments. Figs. 2(e) and 2(f) show that after an initial transient of around 150 time units, which we associate with the dissipation of the pressure gradient present in the initial configuration, the displacement $\Delta x_* = x_*(t) - x_*(0)$ of the interface center increases at constant speed. Both this constant front speed and the two-state equilibration scenario accord with the description of domain growth within the Avrami formalism [12] for crystallization and melting.

Test 4: In our final test we look for evidence that interfacial area is being minimized. In Fig. 1(a), we see a transition from the domain boundary being preferentially aligned along a crystal lattice vector to being aligned horizontally, while in Fig. 1(e), the domain boundary has no particular initial orientation (the surrounding structure is amorphous), but also quickly becomes horizontal. This is evidence of an interfacial energy penalty promoting a reduction of interfacial area. For the slab experiment, the initial width λ_0 of the interface has to do with the abil-




FIG. 2. Dynamics of melting and freezing for temperatures $T_{\text{low}} = 2.0$ and $T_{\text{high}} = 2.1$ tightly straddling the critical point, given an artificial target-state slab at time $t = 0$. (a, b): slice along $z = 0$ of the initial configuration, colored according to Θ on a logarithmic scale from 10^{-3} to 10^{-1} (higher Θ , lighter color). (c, d): average $\Theta(\tilde{x})$ at times $t = 0, 50, \dots, 300$ for melting, and $t = 0, 40, \dots, 400$ for freezing (later time, lighter color). Transparent curves correspond to raw data, solid curves to fits. Here, $\tilde{x} = 2|x|/L_x$, where L_x is the time-dependent system size along the x -axis. (e-h): change, relative to their initial value, of the (e, f) interface center x_* and (g, h) relative width λ/λ_0 obtained when fitting the profiles to Eq. 4. Here, the initial interface width λ_0 has values $\lambda_0 = 0.0213$ and 0.0159 in (e) and (f) respectively. The dashed lines in (e) and (f) are linear fits.

ity of T_0 and T_∞ structure to constrain other structure nearby, but the two-state equilibration scenario means we can associate further growth in λ with roughening of the interface. In Figs. 2(g) and 2(h), after the initial pressure-driven transient ($t \geq 150$), fluctuations in $\Delta\lambda = \lambda(t) - \lambda_0$ are comparable in magnitude to the size of the noise floor. This suppression of roughening is further evidence of an interfacial energy penalty promoting a reduction of interfacial area.

In summary, the results of our four tests match our expectations for a nucleation and domain growth process, validating our methodology.

IV. GLASSES

By adjusting our methodology for calculating Θ (§A 5) and redefining the mobility $\mu(t)$ to be the inherent state

displacement of a given particle between times t and $t + 100$ (accounting for Mermin-Wagner fluctuations as described in §A 6), we can use Θ and μ to characterize the local structure and dynamics of our two-dimensional polydisperse glass.

Test 1: Here we look for growing T_∞ -structure domains in an individual realization of the homogeneous experiment (§B 4). In Fig. 3(a), we see growing high- Θ and matching high- μ domains, representing clear evidence that heating is mediated by domain growth. We do not, however, see any visible low- Θ or low- μ domains during cooling in Fig. 3(e), suggesting a lack of domain growth in this case. This is a first and important difference from the crystal case.

Two-state scenario: Before applying our second test, which will benefit from the results of the slab experiments, we confirm the validity of the two-state scenario. We find good agreement between $1 - f$ calculated from the different structural quantities $P(\Theta)$, \bar{V} , \bar{V}_{IS} , $\bar{\Theta}$, and $\log_{10} \bar{\Theta}$ in Figs. 3(d) and 3(h), establishing the validity of the two-state scenario for both heating and cooling. These figures also highlight a major difference between heating and cooling: the coupling of structure and dynamics. For heating, this coupling is evident from the matching high- Θ and high- μ domains, and the good agreement between $1 - f$ calculated using any of our structural quantities with $1 - f$ calculated from $P(\log_{10} \mu)$ and $\bar{\mu}$ (Fig. 3(d)) demonstrates this yet further. (We do see a deviation from this trend of $1 - f$ calculated from $\log_{10} \bar{\mu}$ due to the rightwards shift of the $P_0(\log_{10} \mu)$ mode with time in Fig. 3(c); see also §B 1.) For cooling, however, $1 - f$ calculated from $\bar{\mu}$ or $\log_{10} \mu$ decays much faster than $1 - f$ calculated from structural quantities (Fig. 3(h)), and while $P(\Theta)$ evolves in accordance with the two-state scenario of Eq. 2 (Fig. 3(f); see also §A 8), the evolution of $P(\log_{10} \mu, t)$, comprising a continuous shift of the initial distribution $P_0(\log_{10} \mu)$ towards lower mobility (Fig. 3(g)), does not. We therefore see that structure and dynamics are decoupled during cooling.

Test 2: Our second test is to look for evidence of a nucleation time. With no evidence of domain growth during cooling, we focus here on heating. We see in Fig. 3(a) that T_{high} -structure domains first appear at time $t \lesssim 10^4$. In a classical nucleation theory scenario, small domains are suppressed, so the nucleation time should be much larger than the time scale of individual rearrangements (successful nucleation should require many attempts), as was the case for the crystal (Fig. 1). We can obtain an estimate of the rearrangement time scale from the time scale for the growth of T_∞ -structure domains, which is a lower bound for the rearrangement time scale within domains of T_{low} -structure. In our slab experiments, we find (Fig. 4(e)) that T_{high} -structure fronts advance with speed 7.85×10^{-4} into the bulk (neglecting deviations of the system size from $L_x = 100$) during heating, corresponding to 1.27×10^3 time units per mean particle diameter. Fronts advancing at this rate into the bulk in




FIG. 3. Heating (a–d) and cooling (e–h) of a two-dimensional polydisperse supercooled liquid between temperatures 0.06 and 0.14. (a, d): snapshots of the mobility μ as the system evolves, exhibiting domain growth during heating and quadrupoles during cooling, once rearrangements are sufficiently rare. (b, c, f, g): evolution of the (b, f) Θ and (c, g) $\log_{10} \mu$ distributions at times (b, c) $t = 6000, 12000, \dots, 60000$ and (f, g) $t = 10^{2.0}, 10^{2.5}, \dots, 10^{6.0}$ (later time, lighter color). The red curves in (f) and (g) are equilibrium distributions, obtained from equilibrium trajectories at the target temperature and pressure. (d, h): untransformed fraction $1 - f$ for f calculated from $P(\log_{10} \Theta)$ (dashed red), $P(\log_{10} \mu)$ (dashed green), \bar{V} (solid orange), \bar{V}_{is} (solid blue), $\bar{\Theta}$ (solid red), $\log_{10} \bar{\Theta}$ (dotted red), $\bar{\mu}$ (solid green), and $\log_{10} \bar{\mu}$ (dotted green).

both the y and $-y$ directions would take 6.36×10^4 time units to cover 100 distance units to span the system, a result consistent with Figs. 3(a) and 3(d). Thus there is no observable separation between the time scale for individual, thermally-activated rearrangements and the time

at which domains of T_{high} -structure are seen to emerge, contrary to what one would expect if nucleation were in play.

Test 3: Here we see if T_{∞} -structure slabs grow in the slab experiment. As we have already mentioned,

$T_\infty = T_{\text{high}}$ -structure slabs indeed grow in heating experiments, with the center of the slab interface, x_* , advancing with constant speed up to the system size limit (Figs. 4(c) and 4(e)). In the case of cooling, however, we see that slabs of $T_\infty = T_{\text{low}}$ structure do not grow at all (Figs. 4(d) and 4(f)). This shows that the reason domains of T_{low} structure are not visible in Fig. 3(e) is that such domains do not grow in the first place. In a classical nucleation theory scenario, the competition between bulk and interfacial free energies would apply to both heating and cooling, with the free energy difference between T_{low} and T_{high} structure in fact being larger during cooling given the lower thermostat temperature $T_\infty = T_{\text{low}}$. This asymmetry and lack of domain growth during cooling is therefore a strong piece of evidence against this scenario.

Test 4: Here we investigate whether the size of the interface is being minimized. The high-mobility domains visible in Fig. 3(a) clearly have rough edges, and we see no alignment along the horizontal axis to minimize the length of the interface. Indeed, spanning the system appears to have no impact on the growth of domains in Fig. 3(a), unlike in the crystal case, where spanning the system was associated with an acceleration of domain growth and alignment of the domain boundaries with the short axis of the system (Figs. 1(a) and 1(e)). The growth of the interface width λ in slab experiments provides further evidence against a thermodynamic drive to minimize the size of the interface. After an early-time transient ($t \lesssim 10^3$) of diffusive growth ($\Delta\lambda \sim t^{1/2}$), we see that that the growth in λ during heating (Fig. 4(g)) is super-diffusive until the time $t \approx 12000$ at which the opposite sides of the slab meet at the periodic boundary. This indicates significant interfacial roughening, faster even than the naïve diffusive expectation for an unsuppressed, freely-diffusing interface.

In summary, the glass behaves very differently from the crystal upon equilibration. All four tests reveal discrepancies between observations and expectations based on a nucleation and growth picture.

V. PLAQUETTE MODELS

Here we show that the very same findings that are inconsistent with a nucleation and growth picture are explained naturally with dynamical facilitation. We mean dynamical facilitation in its broadest sense as the self-propagation of mobility, independent of the mechanisms through which this propagation is achieved. To this end, we apply our four tests to the TPM and SPPM. These models have been shown to display a diverging (at zero temperature) point-to-set length, but the interfacial tension between amorphous metastable states in these systems is zero and their equilibrium dynamics is completely driven by dynamical facilitation, not by RFOT dynamics [65].




FIG. 4. Dynamics of (left column) heating and (right column) cooling supercooled liquids between temperatures $T_{\text{low}} = 0.06$ and $T_{\text{high}} = 0.14$ straddling T_{MCT} , given an artificial target-state slab at time $t = 0$. (a, b): initial configuration for (a) heating and (b) cooling, colored according to Θ on a linear scale from 0.0 to 0.1 (higher Θ , lighter color). (c, d): average $\Theta(\tilde{x})$ at times (c) $t = 0, 2000, \dots, 20000$ and (d) $t = 10^{2.0}, 10^{2.5}, \dots, 10^{6.0}$ (larger time, lighter color). Transparent curves correspond to raw data, solid curves to fits. As before, $\tilde{x} = 2|x|/L_x$, where L_x is the time-dependent size of the system along the x -axis. (e–h): change, relative to their initial value, of the (e, f) interface center x_* and (g, h) relative width λ/λ_0 obtained when fitting the profiles to Eq. 4. Here, the initial interface width λ_0 has values $\lambda_0 = 0.00428$ and 0.00414 in (e) and (f) respectively. The dashed line in (e) is a linear fit, while the dashed line in (g) represents diffusive growth $\sim t^{1/2}$, showing that λ is growing super-diffusively. The dotted curve in (c), and vertical lines in (e) and (g) correspond to time $t = 12000$, above which we judge the left and right boundaries of the slab to interact with one another at the $\tilde{x} = \pm 1$ periodic boundary of the system.

A. Model details

The TPM and SPPM are, respectively, two- and three-dimensional lattice models comprising spins $\sigma_i \in \{-1, 1\}$ (i being the lattice coordinate (i, j) or (i, j, k)) interacting via Hamiltonians

$$H = -\frac{J}{2} \sum_i p_i, \quad (5)$$

where J is the interaction energy and the plaquette $p_i \in \{-1, 1\}$ is the product of the triplet of spins $s_{i-1,j}$, $s_{i-1,j+1}$, and $s_{i,j}$ in the TPM and the quintuplet of spins $s_{i-1,j-1,k+1}$, $s_{i-1,j,k+1}$, $s_{i,j-1,k+1}$, $s_{i,j,k+1}$, and $s_{i,j,k}$ in

the SPPM. We evolve these systems according to Glauber dynamics [66]: nodes are randomly selected, one at a time, to undergo a trial flip $\sigma_i \mapsto -\sigma_i$ with probability

$$P(\text{flip}) = \frac{1}{1 + e^{\beta\Delta E}} \quad (6)$$

of acceptance, where ΔE is the change in energy that would result from this spin flip and $\beta = 1/k_B T$ for temperature T . Given periodic boundary conditions and a number of particles along at least one axis that is a power of two, there is a one-to-one correspondence between spins and plaquettes [50], and it is in the plaquette representation that the TPM and SPPM are seen to be KCMs, with non-interacting Hamiltonians (Eq. 5) and facilitation resulting from the kinetic constraint that trial moves correspond to a triplet of plaquettes $p_{i,j}$, $p_{i+1,j-1}$, and $p_{i+1,j}$ flipping simultaneously in the TPM and a quintuplet of simultaneously flipping plaquettes $p_{i,j,k}$, $p_{i,j,k-1}$, $p_{i,j+1,k-1}$, $p_{i+1,j,k-1}$, and $p_{i+1,j+1,k-1}$ in the SPPM. We take the indices i , j , and k to vary along the x , y , and z axes, respectively, with bond length b separating adjacent nodes along an axis, and adopt b , J , and J/k_B as our length, energy, and temperature units. We assume a constant rate of N trial flips per unit of time, where N is the number of lattice points in the system. For both the TPM and SPPM, we simulate systems with 128 lattice points along each axis.

We once again conduct homogeneous and slab experiments. For the slab experiments, we define our slab to be the set of points with axis coordinate α satisfying $|\alpha| < 12$, where α is the x -coordinate in the TPM case and the z -coordinate in the SPPM case. Since plaquettes do not interact in these systems (Eq. 5), we equilibrate the slab and non-slab regions by randomly sampling the excitation state of each plaquette site with equilibrium probability $1/(1 + e^{1/T})$ of being excited, where $T = T_\infty$ in the slab and T_0 outside the slab. Because the TPM is not invariant under $x \mapsto -x$ and the SPPM is not invariant under $z \mapsto -z$, we treat the interfaces on the left ($\alpha < 0$) and right ($\alpha > 0$) sides of the slab separately.

B. Test results

Test 1: Here we look for growing domains in an individual realization of the slab experiment. As we see in Fig. 5, there is domain growth in both the TPM and SPPM during heating but not during cooling. When present, the domains grow with a characteristic triangular shape set by the kinetic constraint, highlighting the fact that this domain growth is due to dynamical facilitation. This asymmetry of having domain growth during heating but not during cooling is consistent with the results of §IV for the polydisperse glass, and different from the results of §III for a genuine first-order phase transition in the monodisperse system.

Test 2: Here we look for evidence of a nucleation time. Ironically, given that there is by design no nucleation in

these systems (the plaquettes do not interact, so there can be no interfacial tension), the high energy barrier to thermal activation in an excitation-free system means that we do see a significant waiting time of order $t \sim 10^4$ before the emergence of domains, which grow to envelop the system on a time of order $t \sim 10^3$. This waiting time arises due to the need to escape the large potential energy basin of the defect-free initial system in order for domain growth to begin.

Two-state scenario: The TPM and SPPM comprise non-interacting plaquettes in one of two states, so we can safely assume that the results of slab experiments will relate to the behavior seen in the homogeneous experiment. There is therefore no need to test the two-state scenario as we did for the glass and crystal.

Test 3: Here we track domain growth quantitatively in the slab experiment. As we show in Figs. 6(e), 6(f), 6(i), and 6(j), the result of the third test is that slabs in the TPM and SPPM indeed grow upon heating, with the displacement of the interface center from the slab center increasing at a constant rate. The speed at which the center of the left interface advances is different from the corresponding speed for the right interface, as expected given the asymmetric kinetic constraints. By contrast, we see in Figs. 6(g), 6(h), 6(k), and 6(l) that T_∞ -structure slabs in the TPM and SPPM do not grow during cooling, but sometimes even shrink slightly. These results are, once again, consistent with the results of the polydisperse glass.

Test 4: Here we look for evidence of constraints on the roughness of growing domains. During heating, the growing TPM domains in Fig. 5(a) have rough boundaries, but we see little roughness in the growing SPPM domains in Fig. 5(b). There is also no evidence of accelerated domain growth once the system spans the box width, as was seen in Figs. 1(a) and 1(e) for the monodisperse crystal. This is confirmed by the growth of the interface width λ in the slab experiments. As shown in Fig. 6(m), λ grows approximately diffusively during heating in the TPM, while, as seen in Fig. 6(n), the growth of λ in the heated SPPM is strongly sub-diffusive. Despite the similar designs of the TPM and SPPM, the roughness of growing domains during heating has very different dynamics in the two cases. We note that even within a given model, the power law for the growth of λ for the left interface differs from the power law for the right interface. This shows that the asymmetric constraint is affecting the rate of roughening, and highlights the sensitivity of roughening to the mechanism underlying facilitation. The fact that neither the TPM nor the SPPM see the super-diffusive growth of λ seen in the heated polydisperse glass is consistent with this.

We see that the main phenomena associated with the equilibration dynamics of glasses—Avrami-like domain growth during heating and an absence of domains during cooling—can be obtained purely via dynamical facilitation, even with trivial thermodynamics, as in the KCMs studied here, suggesting that these two-state scenario be-




FIG. 5. Structural evolution of the triangular plaquette model (TPM) and square pyramidal plaquette model (SPPM) during heating and cooling. Systems are initialized at equilibrium at temperature $T_0 = 0.0$ for heating (a, b) and 1.0 for cooling (c, d), and the system is then evolved with Glauber dynamics at temperature $T_\infty = 0.3$ (a), 0.5 (b), or 0.2 (c, d). Markers correspond to the locations of excited plaquettes in the given snapshot of the system. In (b), we show a slice along the y -plane containing the largest number of excited plaquettes at time $t = 15000$, so as to capture the birth of the domain. In (d), we instead show a slice along the y -plane containing the smallest number of excited plaquettes at time $t = 10^6$, such that if a low-excitation domain were present at this time, we would capture it.

haviors are generic to dynamically-facilitated systems. The one phenomenon seen in the glass but not recovered in the KCMs is super-diffusive roughening during heating, but this roughening behavior is highly sensitive to the specific details of the system, varying not only between KCMs, but even between the left and right boundaries of a single slab.

C. Phenomenological model

From the shared phenomenology of the polydisperse glass and the KCMs, we can build a minimal, phenomenological model of slab growth,

$$\partial_t c = (c_\infty - c)/\tau + s|\partial_x c| + D\partial_x^2 c, \quad (7)$$




FIG. 6. Dynamics of (left columns) heating and (right columns) cooling the TPM and SPPM from temperature T_0 to T_∞ for $(T_0, T_\infty) = (0.0, 0.3)$ (first column), $(0.0, 0.5)$ (second column), $(0.3, 0.2)$ (third column), and $(0.5, 0.4)$ (last column), given an artificial target-state slab at time $t = 0$. (a–d): initial configuration for (a) TPM heating, (b) SPPM heating, (c) TPM cooling, and (d) SPPM cooling, with markers corresponding to excited plaquettes (in the $y = 0$ plane for the SPPM). The hotter region is shaded red, while the colder region is shaded blue. (e–h): normalized concentration $\tilde{c} = \frac{1}{2} + \frac{c - (c_\infty + c_0)/2}{|c_\infty - c_0|}$ of excited plaquettes within bins of constant x (TPM) or z (SPPM) at times (e) $t = 0, 10000, \dots, 100000$, (f) $t = 0, 1000, \dots, 10000$, (g) $t = 0, 10^3, 10^4, 10^5$, and 10^6 , and (h) $t = 0, 10^1, 10^2, 10^3, 10^4$ and 10^5 (larger time, lighter color). Here, c is the unnormalized concentration, and c_0 and c_∞ are the equilibrium concentrations $1/(1 + e^{1/T})$ for $T = T_0$ and T_∞ , respectively. Transparent curves show raw data, solid curves are fits to Eq. 4. The solid curves fully overlap with the transparent curves, apart from in (g). Bottom rows: change in the fit parameters (i)–(l) x_* and (m)–(p) λ relative to their values in the fit to the $t = 0$ profile. The orange curves correspond to the slab interface initially at negative x , the blue curves to the slab interface initially at positive x . The dashed lines in (i)–(l) are linear fits, the dashed lines in (m)–(p) are power-law fits. There is no blue curve in (o) because it is below the noise floor. The dotted curve in (e), and vertical lines in (i) and (m) correspond to time $t = 50000$, above which we judge the left and right boundaries of the slab to interact with one another.

where c is the excitation state of the system (*e.g.* Θ or the plaquette concentration c), τ is the local relaxation time of the system, s is the speed of mobility propagation (the absolute value ensuring that transport is always directed from high to low mobility), and D is a diffusion constant accounting for the roughening of the system. This allows us to discuss the observed dynamics of these systems in terms of specific dynamical ingredients. For

simplicity, we focus on slab growth in the TPM, identifying the contributions to the rate of change $\partial_t c$ of the plaquette concentration c , and noting system-dependent considerations when they arise.

The first contribution we consider is the mobility propagation $s|\partial_x c|$. In the ultrastable glass heating literature, experiments [24, 28] and a KCM study [67] find front speeds $s = l_s/\tau_\infty (T_\infty)^\gamma$, where $\gamma \approx 1$. Compar-

ing Figs. 4(c) and 6(f) with Figs. 4(i) and 6(j), we see that in both the polydisperse glass and the TPM, the velocity of the interface center remains constant even after significant relaxation of the non-slab region towards equilibrium, so we take l_s to be a constant.

The specific form of the relaxation time τ is system-dependent, but any sufficiently fragile system would yield the speeds $s \approx 0$ for low T_∞ and $s > 0$ for high T_∞ seen in Figs. 4 and 6. From the equilibrium behavior $\tau \sim e^{1/\log(3)T^2}$ [65] of the TPM, we obtain

$$\tau = \tau_0 \exp\left(\frac{1/\log 3}{((1-a)T_\infty + aT_f)^2}\right) \quad (8)$$

by modifying the Tool, Narayanaswami, and Moynihan (TNM) model [68] to yield the TPM relaxation in equilibrium and to work in the limit of vanishing fictive temperature $T_f = 1/\log(c^{-1} - 1)$. Here, τ_0 is a constant time scale and a is a fit parameter (see §B3).

Finally, the rate of roughening is system-dependent, as we have discussed. In the TPM, this roughening yields an approximately diffusive growth of the slab width $\lambda \sim t^{1/2}$, which can be obtained using a diffusive term $D\partial_x^2 c$. From Figs. 4 and 6, we see that when the interface speed is small, so is the diffusion rate, so we assume proportionality between the two, $D = l_D^2/\tau_\infty$, where l_D is a constant.

Comparing Figs. 4 and 7, we see that this phenomenological model of relaxation dynamics based on dynamic facilitation captures the key features of slab evolution, both during heating and during cooling, justifying the separation of dynamics into distinct local relaxation, constant-speed drive, and roughening pieces.

VI. DISCUSSION

We have investigated whether the relaxation of a glass towards equilibrium during heating and cooling proceeds via nucleation and domain growth in the sense of classical nucleation theory. By applying the same four tests to the heating and cooling of a three-dimensional monodisperse crystal, a two-dimensional polydisperse glass, and the TPM and SPPM, we find that the equilibration dynamics of our glass does not resemble that of the melting or freezing crystal, but instead resembles that of the dynamically-facilitated plaquette models in every discriminating aspect.

This is made immediately apparent in Fig. 8, which shows the evolution of $1-f$ calculated from Eq. 3 applied to Θ (8(a)–8(d)) or the plaquette concentration c (8(e)–8(h)) for ten individual homogeneous experiment trajectories (*c.f.* the ensemble-averaged data in Figs. 1, 3, and 5). For crystal melting and freezing in our monodisperse system, we see a nearly discontinuous change of $1-f$ in Figs. 8(a) and 8(b) once a nucleus is formed, though freezing trajectories are seen to get trapped in a number




FIG. 7. Dynamics of the phenomenological model governed by Eq. 7 for constants $l_s = 0.18$ and $l_D = 0.25$ given an artificial target-state slab at time $t = 0$. Heating (left column) is performed between temperatures $T_0 = 0.0$ and 0.3 using $\tau_0 = 0.549$ and $a = 0.253$ and cooling (right column) is performed between temperatures $T_0 = 0.3$ and 0.2 using $\tau_0 = 0.705$ and $a = 1.00$. Parameters are chosen so as to yield behavior similar to the TPM, establishing the reasonableness of this model, but no explicit fit to the TPM is performed. (a, b): normalized excitation state \tilde{c} defined as in Fig. 6(e) at times (a) $t = 0, 1000, \dots, 10000$ and (b) $t = 0, 10^3, 10^4, 10^5$, and 10^6 (larger time, lighter color). Transparent curves correspond to numerically-solved Eq. 7, solid curves to fits to the $x \geq 0$ part of this solution, noting that $c(-x) = c(x)$. (c–f): change, relative to its initial value, of the interface center position x_* (c, d), and width λ (e, f) obtained when fitting the profiles to Eq. 4. The dashed lines in (c) and (d) are linear fits, while those dashed line in (e) and (f) represent diffusive growth $\sim t^{1/2}$.

of metastable states in Fig. 8(b). By contrast, the evolution of $1-f$ in both our polydisperse glass and the two plaquette models (Figs. 8(c)–8(h)) is much smoother and more gradual, reflecting the absence of a nucleation time in these systems. For cooling (Figs. 8(d), 8(f), and 8(h)), the lack of variation between individual trajectories reflects the lack of domain growth in these systems, which results in better averaging within individual realizations.

Fig. 8 highlights the fact that while the absence of a nucleation time and the asymmetry between heating being driven by domain growth and cooling being a homogeneous process is not consistent with a classical nucleation theory scenario, the equilibration dynamics of our glass is in fact generic to dynamically-facilitated systems. Individual trajectories of the glass resemble those of the




FIG. 8. (a–d): Evolution of $1-f$ in homogeneous experiments calculated from Eq. 3 using the mean value of Θ for ten individual realizations contributing to the averaged results shown in (a) Fig. 1(d), (b) Fig. 1(h), (c) Fig. 3(d), and (d) Fig. 3(h). (e–h): Evolution of $1-f$ calculated from Eq. 3 using the concentration c of excited plaquettes for ten individual realizations in the same regimes as those shown in Fig. 5.

plaquette models and not the crystal because dynamical facilitation, not nucleation and domain growth, governs the equilibration dynamics of glasses.

A. Nucleation and Domain growth

While we do find that the equilibration of our glass during heating is mediated by domain growth (Figs. 3, 4, and 8), we do not find evidence of nucleation for either heating or cooling. We find no evidence of a nucleation time for the emergence of T_{high} domains during heating, which appear on a similar time scale to the time scale over which the front of a growing T_{high} domain advances by one mean particle diameter. We also find no evidence of any thermodynamic drive to minimize the total interface between the domains of T_{low} structure and T_{high} struc-

ture during this heating process. Unlike in the crystal case (Figs. 1(a) and 1(e)), there is no alignment of the growing T_{high} domain in Fig. 3(a) along the horizontal axis to minimize its size, and in slab experiments, the slab boundary exhibits super-diffusive roughening. Cooling ultimately provides the most striking evidence against a drive to minimize the interface between domains of T_{high} and T_{low} structure, since the absence of domain growth combined with the validity of the two-state equilibration scenario implies that small domains of T_{low} structure surrounded by T_{high} structure proliferate during the cooling process.

This result concerns only nucleation in the thermodynamic sense of classical nucleation theory. First-order transitions in systems coupled to a reference configuration [3] and dynamical phase transitions [69] are found in KCMs, and an explanation of relaxation dynamics based on those transitions may be possible [4, 54]. As we have shown, however, this explanation cannot involve traditional nucleation and growth, and we believe that it would ultimately boil down to a complementary view on how dynamical facilitation influences relaxation dynamics. Note, moreover, that our results also do not contradict the existence of a finite point-to-set length ξ_{PTS} , nor the possibility of an RFOT mosaic. In fact, the asymmetry between heating and cooling, including the decoupling of structure and mobility during the latter process, can be derived via the microscopic RFOT theory [70, 71]. As shown in §B 2, individual rearrangements perturb the surrounding structure over a length scale $\xi_{\text{perturb}} \sim 10^0$ similar to the point-to-set length $\xi_{\text{PTS}} \sim 10^0$ for our temperature range [35], with the typical size of perturbations to Θ comparable to the size of Θ itself. This raises the possibility that individual rearrangements create individual domains of T_{low} structure within a mosaic as the system cools.

B. Dynamical facilitation

We have established that dynamical facilitation drives the domain growth observed when heating the polydisperse glass. Despite very different mechanisms for dynamical facilitation, the interface center x_* evolves in the same manner in both the polydisperse glass and our two plaquette models. In all cases its behavior is well-captured by a constant-speed driving term $s|\partial_x c|$ in Eq. 7. In recent work, Herrero, Ediger and Berthier [8] conducted very similar slab experiments to ours using the same polydisperse system and find, suggestively, that it is individual rearrangements near the slab boundary that advance the transformation front. They propose a separation of time scales between the mobile T_{high} -structure slab and the immobile T_{low} -structure background that would explain the constant speed of the transformation front, given a constant probability of rearrangement for particles at the leading edge of the front. The validity of the two-state equilibration scenario allows us to relax the

requirement of a separation of time scales, which in turn allows us to explain the constant front speed seen in the slab heating experiments at times $t \geq 10^3$ despite significant relaxation of the non-slab region (Fig. 4(e)). As this region relaxes, domains of T_{high} structure grow which contribute to raising the height of the T_{low} -region plateau in Fig. 4(c) (parameter Θ_0 in Eq. 4), rather than to advancing the front. Instead, the front advances via the transformation of T_{low} -structure adjacent to the front facilitated by rearrangements near the interface. The same scenario explains observations of the same behavior in the TPM (Fig. 6(i)).

The interface width λ , for its part, provides system-specific information. The initial interface widths λ_0 relate to the ability of local structure to constrain structure nearby, hence λ_0 in the crystal (Fig. 2) being larger than in the glass (Fig. 4), while $\lambda_0 \approx 0$ in the non-interacting plaquette systems (Fig. 4). Given the two-state equilibration scenario, the evolution of roughness is captured by the evolution of λ in the ensemble- and spatially-averaged profile $\Theta(\tilde{x})$ (Eq. 4) in slab experiments. As we have seen, this is strongly system-dependent, to the point where the widths of the interfaces on the left and right sides of TPM and SPPM slabs grow as power laws $\lambda \sim t^\nu$ with different power law exponents ν . Among our glass and two plaquette models, we find exponents ν spanning values well above (Fig. 3(g)) to well below (Fig. 5(n)) the naïve diffusive exponent $\nu = 1/2$ for roughness arising from random fluctuations in the local front speed. It was shown in [8] that slab roughness in the slab-experiment heating of very cold systems at very long times reaches a steady state with characteristic length scale set by the dynamic correlation length ξ_4 [72]. Future work may similarly uncover the physical origin of the power-law exponent ν .

C. Technical advances

Our investigations of nucleation and domain growth and dynamical facilitation were aided by two key technical advances with implications of their own. The first was the use of Eqs. 2 and 3 to confirm the two-state equilibration scenario. While, on the basis of heat capacity measurements, this scenario has long been expected to hold for the heating of ultrastable glasses [6, 14, 22, 24, 28, 29, 73], our work here contains the most direct confirmation of the two-state scenario to date, and confirms it for cooling as well as heating, despite the lack of domain growth in the former. This has encouraging implications for the modelling of glasses out of equilibrium, showing that local structure after a rearrangement can simply be sampled directly and independently from the equilibrium distribution of structure at the target equilibrium temperature, as for instance assumed in trap models [74].

A second technical advance of our work is the introduction of the phenomenological model of slab growth, Eq. 7. This model shows how slab growth during heat-

ing can be reconciled with homogeneous relaxation during cooling given the same set of dynamical ingredients. By identifying the distinct components of the dynamics of equilibrating glasses, this model should also aid the development of future models for the equilibration of glasses in non-slab geometries.

ACKNOWLEDGEMENTS

The authors thank C. Scalliet for sharing data sets from [46] with them. R.N.C. is grateful to L. Berthier, H.-H. Boltz, R.C. Dennis, Z. Fakhraai, M.A. Galvani Cunha, C. Herrero, P. Luo, P.D. Olmsted, M. Ozawa, and A.G. Yodh for helpful discussions concerning this project. The design of Figs. 1 and 3 in this paper was heavily inspired by the figures in [75]. This work was supported by the Simons Foundation via the ‘‘Cracking the glass problem’’ collaboration (#454945, RNC and AJL). AJL also thanks the Simons Foundation for support via #327939 as well as for the hospitality of the Center for Computational Biology at the Flatiron Institute, as well as the Isaac Newton Institute for Mathematical Sciences at Cambridge University (EPSRC grant EP/R014601/1), for support and hospitality.

Appendix A: Methodological Details

1. Swap potential

For convenience, we note here that in Eq. 1,

$$c_0 = -28\tilde{r}_{\text{cut}}^{-12} \quad (\text{A1})$$

$$c_1 = 48\tilde{r}_{\text{cut}}^{-14} \quad (\text{A2})$$

$$c_2 = -21\tilde{r}_{\text{cut}}^{-16}, \quad (\text{A3})$$

where $\tilde{r}_{\text{cut}} = 1.25$. We also note that A , σ_{min} , and σ_{max} in the probability density function

$$P(\sigma) = \begin{cases} A\sigma^{-3} & \sigma \in [\sigma_{\text{min}}, \sigma_{\text{max}}] \\ 0 & \text{otherwise} \end{cases} \quad (\text{A4})$$

for the particle size σ can be found by solving

$$2A \tanh\left(\frac{\bar{\sigma}^2(1+c_\sigma^2)}{2A}\right) = \bar{\sigma}^2 \quad (\text{A5})$$

numerically for A and noting that

$$\frac{\sigma_{\text{min}}}{\sigma_{\text{max}}} = \exp\left(-\frac{\bar{\sigma}^2(1+c_\sigma^2)}{A}\right) \quad (\text{A6})$$

and

$$\bar{\sigma} = A(\sigma_{\text{min}}^{-1} - \sigma_{\text{max}}^{-1}), \quad (\text{A7})$$

ultimately yielding

$$A \approx 1.3145271918 \quad (\text{A8})$$

$$\sigma_{\min} \approx 0.7244461244 \quad (\text{A9})$$

$$\sigma_{\max} \approx 1.6138530488 \quad (\text{A10})$$

for $\bar{\sigma} = 1$ and $c_\sigma = 0.23$.

2. Preparation protocols

To homogeneously equilibrate to low temperatures, we conduct Monte Carlo simulations at constant volume and temperature until steady state, randomly selecting particles and conducting trial displacements with components randomly sampled from the interval $(-0.05, 0.05)$. For polydisperse systems, we implement a swap Monte Carlo methodology originally developed by Misaki Ozawa for [35]. With probability 0.2, a trial move corresponds to a trial swap instead of a trial displacement. If a particle with size σ_i is selected for a swap move, a second particle with size σ_j satisfying $|\sigma_j - \sigma_i| < 0.2$ is randomly selected as its swap partner. We start our Monte Carlo simulations from a configuration with random initial positions, except when initializing a crystal in the monodisperse system, in which case we start from a perfect FCC crystal in order to accelerate the equilibration process.

When preparing polydisperse systems containing an artificial target-state slab, we use swap Monte Carlo to equilibrate the system to the target temperature T_∞ . We then designate a slab-shaped region, corresponding to points with x -coordinate satisfying $|x| > a$ for some $a > 0$, to be outside the target-state slab. We choose a new, off-target temperature T_0 for this region, and find the number density for a homogeneous system at equilibrium at temperature T_0 and with virial pressure matching that of the target equilibrium system. We stretch or compress the off-slab region along the x -axis such that it matches this number density, thus reducing the pressure gradient that would otherwise exist between the slab and the non-slab region. MD simulations are then run at the temperature and pressure corresponding to the target equilibrium system.

When preparing monodisperse systems containing an artificial target-state slab, we choose crystal and liquid temperatures that are similar in magnitude, such that the pressure gradient is less pronounced. It is not possible to stretch or compress the off-slab region along the x -axis to reduce the pressure gradient, as we do in the polydisperse case, as this would prevent us from guaranteeing system dimensions compatible with a perfect FCC crystal. We first homogeneously equilibrate the system to the target crystal state, then conduct Monte Carlo simulations at high temperature, sampling only from the liquid region. Once the liquid region has melted, we conduct Monte Carlo simulations at the target, lower temperature for the liquid region, sampling only from this region. MD simulations in this case are run at constant temperature

and a constant pressure chosen such that the virial pressure at equilibrium matches the mean virial pressure in the initial configuration.

3. Molecular dynamics

We conduct our MD simulations in LAMMPS [58] (23 Jun 2022 - Update 2) at constant temperature and pressure implemented via LAMMPS' Nosé-Hoover thermostat (`fix nvt`) with damping parameter `Tdamp = 1` and Berendsen barostat (`fix press/berendsen`) with damping parameter `Pdamp = 1`. If a system has been initialized to temperature T_0 using Monte Carlo, we find the virial contribution to the pressure at this temperature, and choose a pressure such that this contribution is maintained once the temperature changed to the target temperature T_∞ . We do this so as to minimize changes in the system size upon changing the temperature.

4. Initial and steady-state distributions

Because the start-up of the thermostat and barostat perturbs the system at early times, we must wait until a time $t_0 > 0$ before we can measure initial distributions for the homogeneous experiments. We use $t_0 = 55$ for simulations of the monodisperse system and $t_0 = 100$ for the polydisperse system. For homogeneous melting experiments in the monodisperse system, equilibrium distributions are obtained from $t = 600$ data, restricting to realizations with bulk average $\bar{\Theta}(t = 600) > 0.091$. For the homogeneous freezing experiments, ‘‘equilibrium’’ distributions are obtained from $t = 10000$ data. This does not correspond to equilibrium at the target temperature T_{low} , but rather a collection of metastable states that each realization is trapped in at that time (see §VI). For the polydisperse system, equilibrium distributions at temperature $T_\infty = T_{\text{high}}$ are obtained from homogeneous heating experiment data for $t \geq 80000$, while equilibrium distributions at temperature $T_\infty = T_{\text{low}}$ are obtained from simulations at that temperature in the micro-canonical ensemble.

5. Θ

The main structural indicator used in this work is Tong and Tanaka's Θ order parameter [62], which measures how inefficiently packed the structure local to each particle is. For each particle i in the system, we iterate over pairs of nearest neighbors j and k such that j and k are also nearest neighbors of each other. We consider them perfectly efficiently packed if the pair potentials V_{ij} , V_{jk} , and V_{ik} are all equal. If these particles have corresponding sizes σ_i , σ_j and σ_k , this means their centers form a triangle with sides of length $l_{ij} = \frac{1}{2}(\sigma_i + \sigma_j)$,




FIG. 9. Subplot (a): pair distribution $g(\tilde{r})$ for the polydisperse system at temperature $T = 0.14$, calculated separately for particles at the origin of size σ within each of ten logarithmically-spaced bins, plotted as separate curves (larger σ , darker curve). This pair distribution is calculated using the same normalization as the usual pair distribution $g(r)$, but replacing the raw interparticle separation r with \tilde{r} , hence why $g(\tilde{r}) \rightarrow 1$ as $\tilde{r} \rightarrow \infty$. Subplot (b): \tilde{r} -position \tilde{r}_{NN} of the trough following the first nearest neighbor peak of $g(\tilde{r})$ as a function of the diameter σ of the particle at the origin for temperatures $T = 0.06$ (blue crosses) and $T = 0.14$ (orange circles). The dashed line is the linear fit yielding Eq. A14.

$l_{ik} = \frac{1}{2}(\sigma_i + \sigma_k)$ and $l_{jk} = \frac{1}{2}(\sigma_j + \sigma_k)$. At i , this triangle makes an angle θ_{ijk}^* such that

$$\cos \theta_{ijk}^* = \frac{l_{ij}^2 + l_{ik}^2 - l_{jk}^2}{2l_{ij}l_{ik}}. \quad (\text{A11})$$

Letting θ_{ijk} be defined such that

$$\cos \theta_{ijk} = \frac{r_{ij}^2 + r_{ik}^2 - r_{jk}^2}{2r_{ij}r_{ik}}, \quad (\text{A12})$$

where r_{ij} is the distance separating particles i and j , with r_{jk} and r_{ik} defined similarly, we define Θ at i to be

$$\Theta_i = \langle |\theta_{ijk} - \theta_{ijk}^*| \rangle_{j,k}, \quad (\text{A13})$$

where the average is over nearest-neighbor pairs j and k that are nearest neighbors of i as well as each other. The difference in angle $|\theta_{ijk} - \theta_{ijk}^*|$ is calculated modulo π .

For the purposes of calculating Θ_i in our two-dimensional polydisperse system, we consider i and j to be nearest neighbors if they have normalized separation $\tilde{r}_{ij} < \tilde{r}_{\text{NN}}(\sigma_i)$, where

$$\tilde{r}_{\text{NN}}(\sigma_i) = 2.025 - 0.515\sigma_i. \quad (\text{A14})$$

This corresponds to the first minimum after the nearest-neighbor peak of $g(\tilde{r})$, where $g(\tilde{r})$ is proportional to the probability of finding a particle at normalized separation \tilde{r} given a particle at the origin with diameter σ , as shown in Fig. 9. For our three-dimensional monodisperse system, the corresponding quantity is $\tilde{r} = 1.3$. When a particle i does not have any pair of nearest neighbors j and k that are nearest neighbors of each other, we leave its Θ_i undefined and exclude it when calculating averaged quantities.




FIG. 10. Evolution in the canonical ensemble of the mean potential energy of an initially perfect HCP crystal with 22 particles along each basis vector. Curves correspond to temperature $T = 1.5, 1.6, \dots, 5.0$ (lighter color, higher temperature). Time is in units of number of trial Monte Carlo steps per particle.

6. Mermin-Wagner fluctuations

Our two-dimensional glass is influenced by Mermin-Wagner fluctuations [76–78]. We account for this by subtracting from any displacement vector Δp_i of a particle i the mean displacement vector $\langle \Delta p_j \rangle_j$ averaged over neighboring particles $j \neq i$ within a distance ξ of particle i . We choose the value of ξ to be that appropriate to equilibrium at temperature T_∞ , determined as in [11].

7. FCC Ground State

To determine that the ground state of the monodisperse system is an FCC crystal, we reason that the ground state of an isotropic repulsive pair interaction decreasing monotonically with distance must correspond to the distance-maximizing FCC or HCP (hexagonal close packing) structures. As shown in Fig. 10, HCP packings at temperature $T < 2.7$ (thermostat implemented using Monte Carlo trial steps at constant volume) transiently increase in potential energy before relaxing into what we find to be an FCC crystal, implying that the FCC state is more stable. (For $T \geq 2.7$, the packings melt into a liquid instead.)

8. Interpolating distributions

In the main text, we calculate the transformed fraction f from the evolving distribution $P(\phi, t)$ for different quantities ϕ characterizing the local structure or mobility of the system, plotting them as dashed curves in Figs. 1(d), 1(h), 3(d), and 3(h). We achieve this using one of two approaches, depending on the behavior of the growing $P_\infty(\phi)$ mode. When fluctuations in the distribution near the $P_\infty(\phi)$ mode are not too severe, we use

$$f(t) = \frac{P(\phi_*, t) - P_0(\phi_*)}{P_\infty(\phi_*) - P_0(\phi_*)}, \quad (\text{A15})$$




FIG. 11. Validation of Eq. 2. Each row corresponds to data from the main text: (a, b): Fig. 1(b), (c, d): Fig. 1(f), (e, f): Fig. 3(b), (g, h): Fig. 3(f). Left hand side: same data as in the corresponding figure from the main text. Right hand side: output of Eq. 2 (where $\phi = \log_{10} \Theta$ (a–d) or Θ (e–h)) with f calculated from Eq. 3 applied to the quantity Θ .

where $\phi_* = \arg \max_{\phi} P_{\infty}(\phi)$. This is the case for $1 - f$ calculated from $P(\log_{10} \Theta)$ and $P(\log_{10} \mu)$ in Fig. 1(d) (dashed red curve and dashed green curve, respectively), and for $1 - f$ calculated from $P(\Theta)$ in Figs. 3(d) and 3(h) (dashed red curves). However, where the growing $P_{\infty}(\phi)$ mode is sensitive to noise, or where it shifts slightly as it grows (Fig. 3(c)), we use

$$f(t) = \frac{\max_{\phi \in I} P(\phi, t) - \max_{\phi \in I} P_0(\phi)}{\max_{\phi} P_{\infty}(\phi_*) - \max_{\phi \in I} P_0(\phi)}, \quad (\text{A16})$$

which is insensitive to these fluctuations. Here, I is an appropriately-chosen interval. This approach is used to obtain the red and green dashed curves in Fig. 1(d) ($I = (-\infty, -1.75)$ (red) and $(-\infty, -2)$ (green)), as well as the green dashed curve in Fig. 3(d) ($I = (-0.5, \infty)$).

We also calculate f from Eq. 3, using the averages $\bar{\phi}$ of various quantities ϕ and plotting them as solid or dotted curves in Figs. 1(d), 1(h), 3(d), and 3(h). To demonstrate that our different methods of calculating f ,




FIG. 12. Melting transition in a monodisperse system heated from $T_0 = 1.90$ to $T_{\infty} = 2.40$ (*c.f.* $T_{\infty} = 2.35$ in Figs. 1(a)–1(d)). Distributions (a) $P(\log_{10} \Theta)$ and (b) $P(\log_{10} \mu)$ at times $t = 0.0, 3.2, \dots, 48.0$ (later time, lighter curve). (c): untransformed fraction $1 - f$ for f calculated from (dashed red) $P(\log_{10} \Theta)$ and (dashed green) $P(\log_{10} \mu)$, plotted against the mean (solid orange) potential energy V , (solid red) Θ , (dotted red) $\log_{10} \Theta$, (solid green) μ , and (dotted green) $\log_{10} \mu$, affinely transformed according to Eq. 3 with $t_0 = 2.0$. On these short time scales, start-up of the barostat leads to erratic behavior of the inherent state energy, which is therefore not shown.

which collapse onto one another, successfully yield the interpolation parameter f in Eq. 2, we compare in Fig. 11 the evolutions $P(\phi, t)$ shown in Figs. 1(d), 1(h), 3(d), and 3(h) to the evolution obtained from Eq. 2 where $P_0(\phi)$ and $P_{\infty}(\phi)$ are taken as input from simulation data and f is obtained from Eq. 3 using $\phi = \log_{10} \Theta$ (for the crystal) or Θ (for the glass).

Appendix B: Supporting Details

1. Perturbed Crystal

In §III and §IV, we considered systems well-described by the simple interpolation between initial and target states expressed in Eq. 2. We stressed that this implies a clean two-state equilibration scenario, as the systems evolve directly from the initial state into the final state. A good test of this idea is provided by systems in which the initial state is perturbed during the heating process, violating Eq. 2. In Fig. 3, for instance, there is a visible rightwards shift of the $P_0(\log_{10} \mu)$ peak in Fig. 3(c) as target-state domains grow and a corresponding devia-

tion of the decay of the mean of $\log_{10} \mu$ from that of the fraction f of un-transformed structure in Fig. 3(d).

Here, we show in Fig. 12 that slightly increasing the temperature at which we heat our crystal ($T_{\text{high}} = 1.40$, as compared to $T_{\text{high}} = 1.35$ for melting in Fig. 1) leads to large rightwards shifts of the $P_0(\log_{10} \Theta)$ and $P_0(\log_{10} \mu)$ peaks as the melting proceeds (Figs. 12(a) and 12(b)), with corresponding deviations of $1 - f$ calculated from Eq. 3 using the mean values of $\log_{10} \Theta$ and $\log_{10} \mu$ from the correct value of $1 - f$ obtained from the heights of the $P_\infty(\log_{10} \Theta)$ and $P_\infty(\log_{10} \mu)$ peaks (Fig. 12(c)). Inspection of individual trajectories (not shown) suggests that this deviation is due to a large defect density, with pairs of defects imposing strain on crystalline domains trapped between them (note the visible interface of length ≈ 4 particle diameters at the edge of the growing domain in Fig. 1(a), top row).

By contrast, we find that increasing T_{high} to 0.17 in the homogeneous heating of the polydisperse glass, far above the onset temperature [46], does not lead to a perturbation of the un-transformed structure and resultant violation of the two-state equilibration scenario beyond that seen in Fig. 3 for $\log_{10} \mu$. This is likely the result of the highly localized nature of facilitation at low temperatures, as seen in Fig. 3(d) of [11], and the fact that domains of T_{high} and T_{low} do not noticeably statically interact, as we establish in the main text.

2. Structural perturbation due to rearrangements

As the glass evolves during cooling in Fig. 3(e), it becomes possible to distinguish individual rearrangement events from the characteristic quadrupolar displacement fields they induce, as seen in the snapshots at times $t \geq 10^3$. In Fig. 13, we leverage this to identify the effect of such individual rearrangements on the local structure, identifying rearrangements with particles that have mobility $\mu > 0.1$ and have a larger mobility than any other particle within 8 mean particle diameters of distance. We see that changes in Θ near the rearrangement are of the same magnitude $\sim 10^{-1}$ as Θ itself (Figs. 3(b) and 3(b)) up to a distance $r \approx 5$ from the rearrangement, decaying exponentially with decay length $\xi_{\text{perturb}} = 2.34$.

3. Local relaxation in the TPM

Appropriate values for parameters τ_0 and a in Eq. 8 are obtained by fitting Eq. 7 for a homogeneous system to the decay of $\tilde{c}(x = \pm 64)$ towards equilibrium in Figs. 6(e) and 6(g). We show these fits in Fig. 14.

4. Supplemental Movies

In [79], we include supplemental movies for the homogeneous experiments found in the main text, including




FIG. 13. Perturbation to the local Θ field due to rearrangements in the homogeneously cooled glass studied in Figs. 3(e)–3(h) at time $t = 10^6$. (a): Mean absolute change in Θ between times 10^6 and $10^6 + 10^2$ for particles a distance r from a rearranging particle, averaged over ten independent realizations. The inset shows this data on a log-scale after subtracting the global mean absolute change in Θ . The dashed line corresponds to a fit to an exponential decay with decay length $\xi_{\text{perturb}} = 2.43$. (b): Change in Θ across the same time interval as (a) for the realization shown in Fig. 3(e).




FIG. 14. Fits (dashed lines) to the decay of $\tilde{c}(x = \pm 64)$ towards equilibrium in the TPM during (a) heating (6(e)) and (b) cooling (6(g)). In these plots, \tilde{c} is transformed according to Eq. 3 to make the decay clear.

many more snapshots than could be put in the main text. We show multiple realizations of each experiment, with the realization in the main text included as the left-most column. We pair the snapshots with the corresponding evolution of $1 - f$ for the given realization, calculated as in Fig. 8. Supplemental Movie 1 corresponds to Figs. 1(a) and 8(a), Supplemental Movie 2 corresponds to Figs. 1(e) and 8(b), Supplemental Movie 3 corresponds to Figs. 3(a) and 8(c), and Supplemental Movie 4 corresponds to Figs. 3(e) and 8(d). Supplemental Movies 5 and 6 are copies of Supplemental Movies 3 and 4, respectively, but with the Θ plot replaced with the change $\Delta\Theta$ in Θ between times t and $t + 100$.

-
- [1] T. R. Kirkpatrick, D. Thirumalai, and P. G. Wolynes, Scaling concepts for the dynamics of viscous liquids near an ideal glassy state, *Phys. Rev. A* **40**, 1045 (1989).
- [2] I. Douglass and P. Harrowell, Can a stable glass be superheated? Modelling the kinetic stability of coated glassy films, *The Journal of Chemical Physics* **138**, 12A516 (2013).
- [3] L. Berthier and R. L. Jack, Evidence for a Disordered Critical Point in a Glass-Forming Liquid, *Phys. Rev. Lett.* **114**, 205701 (2015).
- [4] R. L. Jack and L. Berthier, The melting of stable glasses is governed by nucleation-and-growth dynamics, *J. Chem. Phys.* **144**, 244506 (2016).
- [5] U. S. Cubeta and V. Sadtchenko, Glass softening kinetics in the limit of high heating rates, *J. Chem. Phys.* **150**, 094508 (2019).
- [6] A. Vila-Costa, J. Ràfols-Ribé, M. González-Silveira, A. F. Lopeandia, g.-i. family=Abad Muñoz, given=LL, and J. Rodríguez-Viejo, Nucleation and Growth of the Supercooled Liquid Phase Control Glass Transition in Bulk Ultrastable Glasses, *Phys. Rev. Lett.* **124**, 076002 (2020).
- [7] C. Herrero, C. Scalliet, M. D. Ediger, and L. Berthier, Two-step devitrification of ultrastable glasses, *Proc. Natl. Acad. Sci. U.S.A.* **120**, e2220824120 (2023).
- [8] C. Herrero, M. D. Ediger, and L. Berthier, Front propagation in ultrastable glasses is dynamically heterogeneous, *The Journal of Chemical Physics* **159**, 114504 (2023).
- [9] J. D. Eshelby, The determination of the elastic field of an ellipsoidal inclusion, and related problems, *Proc. R. Soc. Lond. A* **241**, 376 (1957).
- [10] G. Picard, A. Ajdari, F. Lequeux, and L. Bocquet, Elastic consequences of a single plastic event: A step towards the microscopic modeling of the flow of yield stress fluids, *Eur. Phys. J. E* **15**, 371 (2004).
- [11] R. N. Chacko, F. P. Landes, G. Biroli, O. Dauchot, A. J. Liu, and D. R. Reichman, Elastoplasticity Mediates Dynamical Heterogeneity Below the Mode Coupling Temperature, *Phys. Rev. Lett.* **127**, 048002 (2021).
- [12] M. Fanfoni and M. Tomellini, The Johnson-Mehl-Avrami-Kohnogorov Model: A Brief Review, *Nouv Cim D* **20**, 1171 (1998).
- [13] S. F. Swallen, K. Traynor, R. J. McMahon, M. D. Ediger, and T. E. Mates, Stable Glass Transformation to Supercooled Liquid via Surface-Initiated Growth Front, *Phys. Rev. Lett.* **102**, 065503 (2009).
- [14] K. L. Kearns, K. R. Whitaker, M. D. Ediger, H. Huth, and C. Schick, Observation of low heat capacities for vapor-deposited glasses of indomethacin as determined by AC nanocalorimetry, *The Journal of Chemical Physics* **133**, 014702 (2010).
- [15] K. L. Kearns, M. D. Ediger, H. Huth, and C. Schick, One Micrometer Length Scale Controls Kinetic Stability of Low-Energy Glasses, *J. Phys. Chem. Lett.* **1**, 388 (2010).
- [16] K. J. Dawson, L. Zhu, L. Yu, and M. D. Ediger, Anisotropic Structure and Transformation Kinetics of Vapor-Deposited Indomethacin Glasses, *J. Phys. Chem. B* **115**, 455 (2011).
- [17] K. R. Whitaker, M. Ahrenberg, C. Schick, and M. D. Ediger, Vapor-deposited α,α,β -tris-naphthylbenzene glasses with low heat capacity and high kinetic stability, *The Journal of Chemical Physics* **137**, 154502 (2012).
- [18] A. Sepúlveda, E. Leon-Gutierrez, M. Gonzalez-Silveira, M. T. Clavaguera-Mora, and J. Rodríguez-Viejo, Anomalous Transformation of Vapor-Deposited Highly Stable Glasses of Toluene into Mixed Glassy States by Annealing Above Tg, *J. Phys. Chem. Lett.* **3**, 919 (2012).
- [19] Z. Chen, A. Sepúlveda, M. D. Ediger, and R. Richert, Dynamics of glass-forming liquids. XVI. Observation of ultrastable glass transformation via dielectric spectroscopy, *The Journal of Chemical Physics* **138**, 12A519 (2013).
- [20] A. Sepúlveda, S. F. Swallen, and M. D. Ediger, Manipulating the properties of stable organic glasses using kinetic facilitation, *J. Chem. Phys.* **138**, 12A517 (2013).
- [21] A. Sepúlveda, M. Tylinski, A. Guiseppi-Elie, R. Richert, and M. D. Ediger, Role of Fragility in the Formation of Highly Stable Organic Glasses, *Phys. Rev. Lett.* **113**, 045901 (2014).
- [22] C. Rodríguez-Tinoco, M. Gonzalez-Silveira, J. Ràfols-Ribé, A. F. Lopeandia, M. T. Clavaguera-Mora, and J. Rodríguez-Viejo, Evaluation of Growth Front Velocity in Ultrastable Glasses of Indomethacin over a Wide Temperature Interval, *J. Phys. Chem. B* **118**, 10795 (2014).
- [23] D. Bhattacharya and V. Sadtchenko, Enthalpy and high temperature relaxation kinetics of stable vapor-deposited glasses of toluene, *The Journal of Chemical Physics* **141**, 094502 (2014).
- [24] C. Rodríguez-Tinoco, M. Gonzalez-Silveira, J. Ràfols-Ribé, A. F. Lopeandia, and J. Rodríguez-Viejo, Transformation kinetics of vapor-deposited thin film organic glasses: The role of stability and molecular packing anisotropy, *Phys. Chem. Chem. Phys.* **17**, 31195 (2015).
- [25] S. S. Dalal and M. D. Ediger, Influence of Substrate Temperature on the Transformation Front Velocities That Determine Thermal Stability of Vapor-Deposited Glasses, *J. Phys. Chem. B* **119**, 3875 (2015).
- [26] M. Tylinski, A. Sepúlveda, D. M. Walters, Y. Z. Chua, C. Schick, and M. D. Ediger, Vapor-deposited glasses of methyl-*m*-toluate: How uniform is stable glass transformation?, *The Journal of Chemical Physics* **143**, 244509 (2015).
- [27] D. M. Walters, R. Richert, and M. D. Ediger, Thermal stability of vapor-deposited stable glasses of an organic semiconductor, *The Journal of Chemical Physics* **142**, 134504 (2015).
- [28] J. Ràfols-Ribé, M. Gonzalez-Silveira, C. Rodríguez-Tinoco, and J. Rodríguez-Viejo, The role of thermodynamic stability in the characteristics of the devitrification front of vapour-deposited glasses of toluene, *Phys. Chem. Chem. Phys.* **19**, 11089 (2017).
- [29] U. Cubeta, D. Bhattacharya, and V. Sadtchenko, Communication: Surface-facilitated softening of ordinary and vapor-deposited glasses, *The Journal of Chemical Physics* **147**, 071101 (2017).
- [30] C. J. Fullerton and L. Berthier, Density controls the kinetic stability of ultrastable glasses, *EPL* **119**, 36003 (2017).
- [31] E. Flenner, L. Berthier, P. Charbonneau, and C. J. Fullerton, Front-Mediated Melting of Isotropic Ultrastable Glasses, *Phys. Rev. Lett.* **123**, 175501 (2019).
- [32] M. S. Beasley, C. Bishop, B. J. Kasting, and M. D. Ediger, Vapor-Deposited Ethylbenzene Glasses Approach

- “Ideal Glass” Density, *J. Phys. Chem. Lett.* **10**, 4069 (2019).
- [33] M. Ruiz-Ruiz, A. Vila-Costa, T. Bar, C. Rodríguez-Tinoco, M. Gonzalez-Silveira, J. A. Plaza, J. Alcalá, J. Fraxedas, and J. Rodríguez-Viejo, Real-time microscopy of the relaxation of a glass, *Nat. Phys.*, **1** (2023).
- [34] R. Das, B. P. Bhowmik, A. B. Puthirath, T. N. Narayanan, and S. Karmakar, Soft pinning: Experimental validation of static correlations in supercooled molecular glass-forming liquids, *PNAS Nexus* **2**, pgad277 (2023).
- [35] L. Berthier, P. Charbonneau, A. Ninarello, M. Ozawa, and S. Yaida, Zero-temperature glass transition in two dimensions, *Nat Commun* **10**, 1508 (2019).
- [36] G. Biroli and J. Bouchaud, The Random First-Order Transition Theory of Glasses: A Critical Assessment, in *Structural Glasses and Supercooled Liquids*, edited by P. G. Wolynes and V. Lubchenko (Wiley, 2012) pp. 31–113.
- [37] P. Charbonneau, J. Kurchan, G. Parisi, P. Urbani, and F. Zamponi, Exact theory of dense amorphous hard spheres in high dimension. III. The full replica symmetry breaking solution, *J. Stat. Mech.* **2014**, P10009 (2014).
- [38] J.-P. Bouchaud and G. Biroli, On the Adam-Gibbs-Kirkpatrick-Thirumalai-Wolynes scenario for the viscosity increase in glasses, *The Journal of Chemical Physics* **121**, 7347 (2004).
- [39] G. M. Hocky, L. Berthier, and D. R. Reichman, Equilibrium ultrastable glasses produced by random pinning, *J. Chem. Phys.* **141**, 224503 (2014).
- [40] C. Cammarota, A general approach to systems with randomly pinned particles: Unfolding and clarifying the Random Pinning Glass Transition, *EPL* **101**, 56001 (2013).
- [41] E. R. Weeks, J. C. Crocker, A. C. Levitt, A. Schofield, and D. A. Weitz, Three-Dimensional Direct Imaging of Structural Relaxation Near the Colloidal Glass Transition, *Science* **287**, 627 (2000).
- [42] R. Candelier, A. Widmer-Cooper, J. K. Kummerfeld, O. Dauchot, G. Biroli, P. Harrowell, and D. R. Reichman, Spatiotemporal Hierarchy of Relaxation Events, Dynamical Heterogeneities, and Structural Reorganization in a Supercooled Liquid, *Phys. Rev. Lett.* **105**, 135702 (2010).
- [43] A. S. Keys, L. O. Hedges, J. P. Garrahan, S. C. Glotzer, and D. Chandler, Excitations Are Localized and Relaxation Is Hierarchical in Glass-Forming Liquids, *Phys. Rev. X* **1**, 021013 (2011).
- [44] G. Tarjus, An overview of the theories of the glass transition, in *Dynamical Heterogeneities in Glasses, Colloids, and Granular Media*, edited by L. Berthier, G. Biroli, J.-P. Bouchaud, L. Cipelletti, and W. van Saarloos (Oxford University Press, 2011) pp. 39–67.
- [45] O. Dauchot, D. J. Durian, and M. van Hecke, Dynamical heterogeneities in grains and foams, in *Dynamical Heterogeneities in Glasses, Colloids, and Granular Media*, edited by L. Berthier, G. Biroli, J.-P. Bouchaud, L. Cipelletti, and W. van Saarloos (Oxford University Press, 2011) pp. 203–228.
- [46] C. Scalliet, B. Guiselin, and L. Berthier, Thirty Milliseconds in the Life of a Supercooled Liquid, *Phys. Rev. X* **12**, 041028 (2022).
- [47] J. P. Garrahan, P. Sollich, and C. Toninelli, Kinetically constrained models, in *Dynamical Heterogeneities in Glasses, Colloids, and Granular Media*, edited by L. Berthier, G. Biroli, J.-P. Bouchaud, L. Cipelletti, and W. von Saarloos (Oxford University Press, 2011) pp. 341–369.
- [48] S. Butler and P. Harrowell, Glassy relaxation at surfaces: The correlation length of cooperative motion in the facilitated kinetic Ising model, *The Journal of Chemical Physics* **95**, 4466 (1991).
- [49] R. Gutiérrez and J. P. Garrahan, Front propagation versus bulk relaxation in the annealing dynamics of a kinetically constrained model of ultrastable glasses, *J. Stat. Mech.* **2016**, 074005 (2016).
- [50] J. P. Garrahan and M. E. J. Newman, Glassiness and constrained dynamics of a short-range nondisordered spin model, *Phys. Rev. E* **62**, 7670 (2000).
- [51] D. Kashchiev, *Nucleation: Basic Theory with Applications* (Butterworth Heinemann, 2000).
- [52] J. P. Garrahan, Glassiness through the emergence of effective dynamical constraints in interacting systems, *J. Phys.: Condens. Matter* **14**, 1571 (2002).
- [53] J. P. Garrahan, Transition in coupled replicas may not imply a finite-temperature ideal glass transition in glass-forming systems, *Phys. Rev. E* **89**, 030301 (2014).
- [54] R. M. Turner, R. L. Jack, and J. P. Garrahan, Overlap and activity glass transitions in plaquette spin models with hierarchical dynamics, *Phys. Rev. E* **92**, 022115 (2015).
- [55] F. Ritort and P. Sollich, Glassy dynamics of kinetically constrained models, *Advances in Physics* **52**, 219 (2003).
- [56] A. Ninarello, L. Berthier, and D. Coslovich, Models and Algorithms for the Next Generation of Glass Transition Studies, *Phys. Rev. X* **7**, 021039 (2017).
- [57] S. Sengupta, T. B. Schröder, and S. Sastry, Density-temperature scaling of the fragility in a model glass-former, *Eur. Phys. J. E* **36**, 141 (2013).
- [58] S. Plimpton, Fast Parallel Algorithms for Short-Range Molecular Dynamics, *Journal of Computational Physics* **117**, 1 (1995).
- [59] Y. Peng, W. Li, T. Still, A. G. Yodh, and Y. Han, In situ observation of coalescence of nuclei in colloidal crystal-crystal transitions, *Nat Commun* **14**, 4905 (2023).
- [60] R. L. Penn and J. F. Banfield, Imperfect Oriented Attachment: Dislocation Generation in Defect-Free Nanocrystals, *Science* **281**, 969 (1998).
- [61] R. L. Penn and J. F. Banfield, Oriented attachment and growth, twinning, polytypism, and formation of metastable phases; insights from nanocrystalline TiO₂, *American Mineralogist* **83**, 1077 (1998).
- [62] H. Tong and H. Tanaka, Revealing Hidden Structural Order Controlling Both Fast and Slow Glassy Dynamics in Supercooled Liquids, *Phys. Rev. X* **8**, 011041 (2018).
- [63] Note that $P_0(\log_{10} \Theta)$ for heating is not the same as $P_\infty(\log_{10} \Theta)$ for cooling, since a randomly-nucleated crystal is unlikely to be oriented in a direction compatible with the system axes, so equilibrium at the perfect FCC crystal structure is not generally attainable upon cooling.
- [64] Symmetry-breaking sample-to-sample fluctuations are suppressed upon ensemble averaging in practice, and in the limit of infinite size along the y and z axes in principle.
- [65] R. L. Jack and J. P. Garrahan, Caging and mosaic length scales in plaquette spin models of glasses, *The Journal of Chemical Physics* **123**, 164508 (2005).

- [66] R. J. Glauber, Time-Dependent Statistics of the Ising Model, *Journal of Mathematical Physics* **4**, 294 (1963).
- [67] S. Léonard and P. Harrowell, Macroscopic facilitation of glassy relaxation kinetics: Ultrastable glass films with frontlike thermal response, *J. Chem. Phys.* **133**, 244502 (2010).
- [68] C. T. Moynihan, A. J. Eastale, M. A. De BOLT, and J. Tucker, Dependence of the Fictive Temperature of Glass on Cooling Rate, *Journal of the American Ceramic Society* **59**, 12 (1976).
- [69] L. O. Hedges, R. L. Jack, J. P. Garrahan, and D. Chandler, Dynamic Order-Disorder in Atomistic Models of Structural Glass Formers, *Science* **323**, 1309 (2009).
- [70] V. Lubchenko and P. G. Wolynes, Theory of Structural Glasses and Supercooled Liquids, *Annu. Rev. Phys. Chem.* **58**, 235 (2007).
- [71] P. G. Wolynes, Spatiotemporal structures in aging and rejuvenating glasses, *Proc. Natl. Acad. Sci. U.S.A.* **106**, 1353 (2009).
- [72] N. Lačević, F. W. Starr, T. B. Schröder, and S. C. Glotzer, Spatially heterogeneous dynamics investigated via a time-dependent four-point density correlation function, *The Journal of Chemical Physics* **119**, 7372 (2003).
- [73] C. Rodríguez-Tinoco, M. Gonzalez-Silveira, J. Ràfols-Ribé, A. Vila-Costa, J. C. Martinez-Garcia, and J. Rodríguez-Viejo, Surface-Bulk Interplay in Vapor-Deposited Glasses: Crossover Length and the Origin of Front Transformation, *Phys. Rev. Lett.* **123**, 155501 (2019).
- [74] C. Monthus and J.-P. Bouchaud, Models of traps and glass phenomenology, *J. Phys. A: Math. Gen.* **29**, 3847 (1996).
- [75] A. Chardac, L. A. Hoffmann, Y. Poupart, L. Giomi, and D. Bartolo, Topology-Driven Ordering of Flocking Matter, *Phys. Rev. X* **11**, 031069 (2021).
- [76] E. Flenner and G. Szamel, Fundamental differences between glassy dynamics in two and three dimensions, *Nat Commun* **6**, 7392 (2015).
- [77] S. Vivek, C. P. Kelleher, P. M. Chaikin, and E. R. Weeks, Long-wavelength fluctuations and the glass transition in two dimensions and three dimensions, *Proc. Natl. Acad. Sci. U.S.A.* **114**, 1850 (2017).
- [78] B. Illing, S. Fritschi, H. Kaiser, C. L. Klix, G. Maret, and P. Keim, Mermin–Wagner fluctuations in 2D amorphous solids, *Proc. Natl. Acad. Sci. U.S.A.* **114**, 1856 (2017).
- [79] See Supplemental Material for six supplemental movies.